

Article	Finishing number	Design number	Issuing date	27.06.2023
Supplier's article	47015 9645	7056	Expire on	
Article name	Carol Print *Jardin*		Season	
Customer's article			Minimum quantity	
			Price	

CUSTOMER	SUPPLIER
Customer No	Supplier No
Customer	Supplier
Street	Street
Post code	Post code
Town	Town
Country	Country
Telephone	Telephone
Approval Date	

1. CONSTRUCTION CHARACTERISTICS	SUPPLIER'S FEATURES	TEST METHOD
Material composition - according to the law	100% VI	DIN 54200 ff
Pile composition	100% VI	
Weight g/sqm - g/m	284 g/sqm	DIN EN 1212
Average length of piece	33 m	
Make up	on frame	
Overall width	139 cm	EN 1773
Minimum useful width	135 cm	EN 1773
Expected number of faults	max 8	

2. FINISH CHARACTERISTICS	SUPPLIER'S FEATURES
Type of dyeing	<input checked="" type="checkbox"/> Piece dyed <input type="checkbox"/> Yarn dyed <input type="checkbox"/> Printed
Special type finish	<input type="checkbox"/> Prepared for dyeing <input type="checkbox"/> Prepared for printing <input type="checkbox"/> Garment wash
Coating / kind of coating	<input type="checkbox"/> Yes <input checked="" type="checkbox"/> No
Class of dyestuff for all colors	<input type="checkbox"/> Reactive <input type="checkbox"/> Acid <input checked="" type="checkbox"/> Direct <input type="checkbox"/> Pigment <input type="checkbox"/> Sulphur <input type="checkbox"/> Disperse
Cationic dyeing / industrial laundry	<input type="checkbox"/> Yes <input type="checkbox"/> No <input checked="" type="checkbox"/> Please contact us
Optical brightened	<input type="checkbox"/> Yes <input type="checkbox"/> No <input checked="" type="checkbox"/> Please contact us
Fusibility	<input type="checkbox"/> Yes <input type="checkbox"/> No <input checked="" type="checkbox"/> Please contact us
PH value	4-8
Formaldehyde	<= 75 ppm

3. PROCESSING CHARACTERISTICS	SUPPLIER'S FEATURES	TEST METHOD
Unicolored	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No	
Napped goods	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No	
HORIZONTAL repetition size of pattern		
VERTICAL repetition size of pattern		
Extention of printed borders	Right (cm) Left (cm)	
Printed borders of constant width	<input type="checkbox"/> Yes <input type="checkbox"/> No	
Bias distortion (skewing)	2,5%	BS 2819

4. MAINTENANCE'S INSTRUCTIONS OF THE FABRIC	
---	--

Washing, Chlorination, Ironing, Dry cleaning		CARE SYMBOLS DEFINITION ISO 3758, DIN EN 23758
Tumbling, Wet cleaning, Add recommendations		

5. MECHANICAL AND PHYSICAL PROPERTIES	SUPPLIER'S FEATURES	TEST METHOD
Extention (elastic material)	Warp > Weft >	Herberlein
Permanent extention (elastic material)	Warp > Weft >	Du Pont
Tear strength	Warp > 1 daN Weft > 1 daN	EN ISO 13937 -2
Tensile strength stripes	Warp > 25 daN Weft > 25 daN	EN ISO 13934 -1
Seam shifting resistance (2mm)	Warp > 2 daN Weft > 2 daN	EN ISO 13936 -1
Seam shifting resistance GB Standard	Warp > Weft >	
Seam shifting resistance GB Standard	Warp > Weft >	
Abrasion fastness (Martindale Apparel 9 KPa)	Round: 20000/2	DIN EN ISO 12947-2
Fabric propensity to surf. Fuzzing and Pilling - GB Standard	Evaluation: <input type="checkbox"/>	DIN EN ISO 12947-2
Crease tendency / recovery	3	ISO 9867
Water repellent / spray test	1	EN 24920

